

## DINITROL 6070

Plastic Contour Putty

### Characteristics:

A 2-component smooth paste-like putty, especially suitable for the subsequent treatment of repaired plastic components. Based on its smooth consistency, profiles and contours on damaged and bonded plastic parts can be renovated with ease.

Elastic, rapid drying time, easy to file, pore-free, good adhesion to plastics and bodywork and zinc-coated sheets, matt burnished 2-c lacquers, glass fibre reinforced plastics (polyester and epoxy films).

### Areas of Application:

After appropriate pre-treatment, this contour putty adheres well to practically all plastics used in the vehicle sector.

Not suitable for use on: Soft PVC, hard rubber, thermoplastic lacquers, PTFE, Viton, nitro lacquers and polystyrol.

### Method of Use:

Clean and dry the surface to be repaired.

Mix the required amount of putty with 2 – 3% hardener and apply.

The working time (pot life) is 5 minutes.

After a further 20 – 30 minutes, DINITROL 6070 can be filed.

### Technical data:

Colour:	dark grey
Base:	unsaturated polyester resin
Hardening system:	Dibenzoyl peroxide
Density:	1.8 g/cm <sup>3</sup>
Flash point:	< 31°C
Processing temperature:	15°C – 25°C
Storage time:	12 months (between 15°C and 25°C)
Delivery form:	500 g

Note: Seal opened packages immediately after use.

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telephone:  
+49 (0) 52 81 / 9 82 98-0  
Fax:  
+49 (0) 52 81 / 9 82 98-60  
Email:  
service@dinol.com